



1001 Trout Brook Crossing
Rocky Hill, CT 06067-3910
Telephone: (860) 571-5100
FAX: (860) 571-5465

Product Description Sheet

Product 790

Industrial Version, January 1999

PRODUCT DESCRIPTION

LOCTITE® Product 790 Chisel® Gasket Remover lifts off baked-on gaskets, gasket cements, formed-in-place gaskets, carbon deposits, dried oil, grease and paint on any type of metal in minutes. Also suitable for use on wood.

PRODUCT FEATURES

Product 790 Chisel® Gasket Remover is a chemical liquid that works to remove pre-cut conventional gasket cements as well as formed-in-place chemical gaskets.

It is packaged in a convenient spray liquid that penetrates and cleans intricate shapes and will not run off, even on vertical surfaces.

Product 790 Chisel® Gasket Remover is ideal for removing:

- Baked-on gaskets and gasket cements from any type of metal surface.
- Chemical formed-in-place gaskets, including RTV silicone and anaerobic materials.
- Gaskets from aluminum components without scraping or damaging machine surfaces.
- Gaskets from small to difficult-to-reach components.
- High temperature engine paints prior to repainting.
- Built-up carbon deposits from interior engine/combustion surfaces.
- Baked-on grease and oil deposits (excellent pre-cleaner prior to solvent washing - keeps solvent baths cleaner, longer).
- Paint and varnish from wood surfaces (excellent for removing surface coating from delicate wood, carved surfaces without scraping or damaging surfaces).

DIRECTIONS FOR USE

1. Hold can upright 10 - 12 inches from gasket area to be sprayed.
2. Spray area to be stripped - the heavier the coat, the better.
3. Allow 5 - 10 minutes for foaming action of Loctite 790 Chisel Gasket Remover to destroy old gasket.
4. Remove old gasket or gasket cement with a scraper or putty knife. Wipe flange clean with a rag. Repeat procedure if necessary.
5. Prior to assembly with new gasket, spray all surfaces clean with Loctite ODC-Free Cleaner.
6. After use, turn can upside down and spray for 3 seconds to clear actuator.

TYPICAL PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Methylene Chloride
Appearance	Foamy, white liquid
Specific Gravity	0.9
Flash Point, °F	-142

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected with a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet. (MSDS).

Storage

Product shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C (46°F to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container. For further specific shelf life information, contact your local Technical Service Center.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Loctite Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loctite Corporation's products. Loctite Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Loctite Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

NOT FOR PRODUCT SPECIFICATIONS
THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.
PLEASE CONTACT LOCTITE CORPORATION QUALITY DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT.
ROCKY HILL, CT FAX: +1 (860)-571-5473 DUBLIN, IRELAND FAX: +353-(1)-451 - 9959